RG104 E-1 Box 121

21.

Weekly Report of Gold Deposits Melted at United States Mint.

1880

Date.	Assay No.	Name of Depositor.	Weight before Melting. oz.	dec.	Weight after Melting. oz.	dec.	Loss. oz.	dec.	Loss per ct.	Gain. oz.	dec.	Description of Bullion.
May 17th	797	G. C. Thompson	25	25	23	65	1	60	6 40			Watch Cases & Jewelry
	8	Do	5	44	5	44						Bar, Va.
	9	Do	20	13	20	11		03	15			Buttons
	800	Do	20	34	17	39	2	95	14 75			Jewelry, Watch Cases
	1	Do	3	54	3	54						Burnt Coin & Pieces
	2	R. Levy	39	31	39	28		03	08			Bars
	3	Wm. H. Lee	64	32	64	29		03	05			Bar
	4	E. Kretzmar	8	58	8	43		15	1 67			Button
	5	Thos. R. Lee	70	88	70	83		05	07			Bar
	6	Theo. Kitchen, Exch.	7	10	7	06		04	57			Bar & Button
18th	7	G. C. Thompson	6	19	5	83		36	6 00			Leaf & Button
	8	Do	10	55	9	56		99	9 00			Watch Cases & Jewelry
	9	McCall & Newman	71	30	66	95	4	35	6 13			Buttons
	10	Drexel & Co.	12	56	12	56						For. Coin
	1	A. Loudon Snowden, Supt.	132	87	132	86		01	008			Bars, U.S.A.O.N.C.
	2	Lingg & Bro.	19	85	13	90	5	95	29 75			Buttons, Base
	3	G. C. Thompson	17	05	17	00		05	29			Bar
19th	4	Do	28	98	27	29	1	69	5 83			Jewelry & Silver
	5	Emory, Breed & Co.	15	97	15	97						For. & U.S. Coin
	6	L. A. Ford	30	47	26	90	3	57	11 90			Watch Cases & Jewelry
20th	7	G. C. Thompson	27	48	24	91	2	57	9 52			Jewelry, Watch Cases
	8	Wm. Rutter & Co.	9	05	5	97	3	08	34 22			Leaf
21st	9	Phillips & Jacobs	69	85	69	85						For. Coin
	20	Do	265	18	265	00		18	07			Bars
22nd	1	G. C. Thompson	5	93	5	97					04	Jewelry, Watch Case
	2	Do	6	24	6	23		01	17			Button, Gen.
	3	Do	26	70	19	94	6	76	25 04			Bars & Silver, Base
	4	H. Muhr's Sons	13	20	13	20						Bars
	5	Newlin Bros.	5	52	5	52						Bar
	6	G. C. Thompson	159	95	142	04	17	91	11 19			Bars, Base
	7	J. C. White	18	81	18	19		62	3 26			D. P., Fillings & Filings [?]
	8	C. & A. Pequignot	90	62	90	58		04	05			Bar
	9	A. K. Curtis	91	29	88	31	2	98	3 27			Grs., Sps. & Jewelry, Africa
			1400	50	1344	54	56	00	4 40		04	

Notes of Melter & Refiner. 26/5/80

The deposits are from the following sources:

Africa	1
Finer bullion	13
Baser "	4
Jewelry, &c.	7
very base	4
Coin	4
Total	33

The African grains suffered their usual wastage of 3.27%: — the finer bullion, lost the low rate of 0.13%; the baser lost fairly at 4¼%: — the jewelry lost moderately at 8.20%; — the very base lost at about its usual rate 25.05%. — The usual return of no loss in coin of 100 oz. weight is objectionable, because it cannot be melted without loss, and so the Government bears the loss.

Jas. C. Booth } M. & R. }

For week ending May 22nd 1880

Approximate value, $ 20,840,37

To the Director of the Mint.

J. Robley Dunglison Register.

RG104 E-1 Box 121

Report of Gold Deposits
melted for week ending
May 22nd 1880

NARA RG104, Entry 1, Box 121

[Abstract:] Report of Gold Deposits melted for weeks ending: -

May 22, 1880

Weekly Report of Gold Melted at United States Mint.

[Please see original images for data table.]